

Technical Data Sheet

TT700

THERMAL TRANSFER GLOSSY WHITE POLYESTER FILM

GENERAL TT700 is a topcoated glossy white polyester film. It is coated with

DESCRIPTION: an aggressive permanent acrylic adhesive and backed with a 50# Kraft release liner.

USES: Ideal for nameplates or serial identification labels on finished products. TT700 is

UL/CSA recognized with certain thermal transfer resin ribbons. Other applications include rating plates, property identification, electronic component marketing and industrial bar code applications requiring durability. Excellent material to be used on the topside of a circuit board where heat exposure is limited. This high-performance material is designed for applications requiring excellent solvent and scratch resistance.

FEATURES: Indoor/outdoor, smudge- and abrasion-resistant thermal images using resin-based

ribbons, dimensionally stable film (no shrinkage), high-performance adhesive. Topcoat and ribbon combinations offer excellent scratch and solvent resistance. TT700 does have some limited static dissipating properties. TTRR-V and TTRR-N

are not UL/CSA approved on this material.

AGENCY UL-MH16873 CSA- LS-89882-6

APPROVAL:

THICKNESS:

RECOMMENDED

RIBBON: TTRR-D, TTRR-C, TTRR-S, TTRR-N and TTRR-V

PHYSICAL TEST METHODS CONVENTIONAL S.I. UNITS

PROPERTIES: UNITS

Film 2.0 mils 50.8 microns Adhesive 0.8-0.9 mils 20-23 microns Liner (50#) 3.0 mils 75 microns

Total 5.8-5.9 mils 145.8-148.8 microns

ADHESIVE Stainless Steel 67 oz/in 737 N/m **PERFORMANCE:** Acrylic 71 oz/in 781 N/m

Polypropylene 48 oz/in 528 N/m Glass 69 oz/in 759 N/m

ADHESIVE PERFORMANCE AFTER A 72 HOUR DWELL

SERVICE TEMPERATURE: -40°F - 302°F -40°C - 150°C

MINIMUM APPLICATION TEMPERATURE: 50°F 10°C

EXTERIOR 2 yrs. outdoor Label Stock: No Effect

DURABILITY: exposure Label Stock with TTRR-D Ribbon printing: No Effect

CHEMICAL RESISTANCE:

Test should be conducted at room temperature after 24 hour dwell. Testing should consist of five cycles of 10 minute immersions in the specified chemical reagent followed by 30 minute recovery periods. Cotton swab rub prior to final immersion.

CHEMICAL REAGENT: LABEL STOCK: PRINTING: PRINTING:

(without printing) (using TTRR-D ribbon) (cotton swab rub)

| Household Cleaners | No effect | No effect | No effect |
|--------------------|-----------|---------------|---------------|
| Oil | No effect | No effect | No effect |
| Water | No effect | No effect | No effect |
| Isopropyl Alcohol | No effect | No effect | No effect |
| Mild Acid | No effect | No effect | No effect |
| Mineral Spirits | No effect | No effect | No effect |
| Toluene | No effect | Print removed | Print removed |

STORAGE STABILITY Product should be stored at 70°F (21°C) and 40-50% relative humidity

to ensure optimal performance.

SHELF LIFE: 2 years @ proper storage conditions.